

TAD Metals Inc.

Correspondence table for stainless steel designations

UNI (Italy) UNI 6900-71 November 1971	AISI (USA) Ed. 1974	SIS (Sweden) MNC 900 E	BSI (Great Britain) BSI PD 6290 December 1967	DIN (Germany)		EURONORM Economic Community Carbon and Steel Euronorm 88-71 Sett. 1971
				Designation DIN 17006	W.N. DIN17007	
-	201	-	-	-	-	-
-	202	-	-	-	-	-
-	205	-	-	-	-	-
X 12 CrNi 17 07	301	23 31	301 S 01	-	-	X 12 CrNi 17 7
X 10 CrNi 18 09	302	23 31	302 S 02	-	-	X 10 CrNi 18 9
-	302B	-	-	-	-	-
X 10 CrNiS 18 09	303	-	303 S 21	X 12 CrNiS 18 8	1.4305	X 10 CrNiS 18 9
X 10 CrNiS 18 09	303 Se	-	303 S 41	-	-	-
X 5 CrNi 18 10	304	23 32	304 S 01	X 5 CrNi 18 9	1.4301	X 6 CrNi 18 10
-	-	-	-	X 5 CrNi 19 11	1.4303	-
-	304N	23 70	-	-	-	-
X 8 CrNi 19 10	-	-	-	-	-	-
X 2 CrNi 18 11	304L	23 52	304 S 12	X 2 CrNi 18 9	1.4306	X 8 CrNi 18 10
-	-	23 71	-	X 2 CrNi 18 10	1.4311	-
X 8 CrNi 18 12	305	23 33	305 S 01	-	-	X 8 CrNi 18 12
-	308	-	-	-	-	-
X 16 CrNi 23 14	309	-	309 S 01	X 15 CrNiSi 20 12	1.4828	-
X 6 CrNi 23 14	309S	-	-	-	-	-
X 22 CrNi 25 20	310	-	310 S 24	X 12 CrNi 25 21	1.4845	-
X 6 CrNi 25 20	310S	23 61	-	-	-	-
X 16 CrNiSi 25 20	314	-	-	X 15 CrNiSi 25 20	1.4841	-
X 5 CrNiMo 17 12	316	23 47	316 S 01	X 5 CrNiMo 18 10	1.4401	X 6 CrNiMo 17 12 2
X 5 CrNiMo 17 13	316	23 43	316 S 01	X 5 CrNiMo 18 12	1.4436	X 6 CrNiMo 17 13 3
-	316F	-	-	-	-	-
X 2 CrNiMo 17 12	316L	-	316 S 12	X 2 CrNiMo 18 10	1.4404	X 3 CrNiMo 17 12 2
-	-	-	-	X 2 CrNiMoN 18 12	1.4406	-
X 2 CrNiMo 17 13	316L	23 53	316 S 12	X 2 CrNiMo 18 12	1.4435	X 3 CrNiMo 17 13 3
-	-	23 75	-	X 2 CrNiMoN 18 13	1.4429	-
-	316N	23 74	-	-	-	-
X 6 CrNiMoTi 17 12	-	-	320 S 01	X 10 CrNiMoTi 18 10	1.4571	X 6 CrNiMoTi 17 12 2
X 6 CrNiMoTi 17 13	-	-	320 S 01	-	-	X 6 CrNiMoTi 17 13 3
X 6 CrNiMoNb 17 12	-	-	318 S 01	X 10 CrNiMoNb 18 10	1.4580	X 6 CrNiMoNb 17 12 2
X 6 CrNiMoNb 17 13	-	-	318 S 01	-	-	X 6 CrNiMoNb 17 13 3
-	317	23 66	317 S 01	-	-	-
X 2 CrNiMo 18 16	317L	23 67	-	X 2 CrNiMo 18 16	1.4438	X 3 CrNiMo 18 16 4
X 6 CrNiTi 18 11	321	23 37	321 S 12	X 10 CrNiTi 18 9	1.4541	X 6 CrNiTi 18 10
X 8 CrNiTi 18 11	-	-	321 S 12	-	-	-
-	329	-	-	-	-	-
-	330	-	-	-	-	-

TAD Metals Inc.

Correspondence table for stainless steel designations

X 6 CrNiNb 18 11	347	23 38	347 S 01	X 10 CrNiNb 18 9	1.4550	X 6 CrNiNb 18 10
X 8 CrNiNb 18 11	-	-	347 S 01	-	-	-
-	348	-	-	-	-	-
-	384	-	-	-	-	-
X 12 Cr 13	403	23 02	403 S 17	X 7 Cr 13	1.4000	X 12 Cr 13
-	-	-	-	X 10 Cr 13	1.4006	-
-	-	-	-	X 15 Cr 13	1.4024	-
X 6 CrAl 13	405	-	405 S 01	X 7 CrAl 13	1.4002	X 6 CrAl 13
X 10 CrAl 12	-	-	-	X 10 CrAl 13	1.4724	-
-	-	-	-	X 10 CrAl 18	1.4742	-
-	-	-	-	-	-	-
-	409	-	-	-	-	-
X 12 Cr 13	410	23 02	410 S 01	X 7 Cr 13	1.4000	X 12 Cr 13
-	-	-	-	X 10 Cr 13	1.4006	-
-	-	-	-	X 15 Cr 13	1.4024	-
X 6 Cr 13	-	-	403 S 17	X 7 Cr 13	1.4000	X 6 Cr 13
-	-	-	-	-	-	-
-	414	-	-	-	-	-
X 12 CrS 13	416	-	416 S 21	-	-	X12 CrS 13
X12 CrS 13	416 Se	-	416 S 41	-	-	-
X 20 Cr 13	420	23 03	420 S 29	X 20 Cr 13	1.4021	X 20 Cr 13
X 30 Cr 13	420	23 04	420 S 45	-	-	X 30 Cr 13
X 40 Cr 14	420	-	420 S 01	X 40 Cr 13	1.4034	X 40 Cr 13
-	420 F	-	-	-	-	-
-	422	-	-	-	-	-
-	-	-	-	X 20 CrMoV 12 1	1.4922	-
-	429	-	-	-	-	-
-	-	23 01	-	X 7 Cr 14	1.4001	-
X 8 Cr 17	430	23 20	430 S 15	X 8 Cr 17	1.4016	X 8 Cr 17
-	-	-	-	X 8 CrTi 17	1.4510	X 8 CrTi 17
X 10 CrS 17	430F	-	441 S 01	X 12 CrMoS 17	1.4104	X 10 CrS 17
X 10 CrS 17	430 F Se	-	-	-	-	-
X 14 CrNi 19	-	-	442 S 01	-	-	-
X 16 CrNi 16	431	23 21	431 S 01	X 22 CrNi 17	1.4057	X 21 CrNi 17
X 8 CrMo 17	434	-	432 S 19	X 6 CrMo 17	1.4113	X 8 CrMo 17
-	436	-	-	-	-	-
-	440 A	-	-	-	-	-
-	440 B	-	-	-	-	-
-	440 C	-	-	-	-	X 105 CrMo 17
-	442	-	442 S 01	-	-	-
-	-	-	-	X 10 CrAl 24	1.4762	-
X 16 Cr 26	446	23 22	-	-	-	-